

## ☒48. Polystyrene Oligomers

Sample: PS 580  
Column: PLRP-S 100Å 5µm, 250 × 4.6mm (1512-5500)  
Eluent A: Water  
Eluent B: THF  
Gradient: 65 - 85% B in 40 mins  
Flow Rate: 0.5ml/min  
Detector: PL-ELS 1000 (neb=60°C,  
evap=85°C, gas=0.8 SLM)

